

GEARSYN AW SERIES

INDUSTRIAL SYNTHETIC AW GEAR LUBRICANTS

GEARSYN AW SERIES gear lubricants are fully synthetic and have been formulated from premium polyalphaolefins (PAO) base fluids for enclosed gear systems requiring ashless antioxidants and anti-wear. These oils have been designed to provide proper lubrication under hydrodynamic and mild boundary lubrication conditions. They are recommended for gear systems and bearings where moderate loads, high temperatures and humidity are expected, including worm gears containing soft metal such as bronze, brass and copper.

PRODUCT APPLICATIONS:

- The **GEARSYN AW SERIES** lubricants are multipurpose lubricants that can be used for a wide variety of industrial applications.
- They are similar to petroleum oils in their compatibility to seals, hoses, gaskets and paint.

<i>Enclosed Gear Units: Spur, Helical, Bevel & Worm Gears</i>	<i>Circulating and Splash Lubricated Systems</i>	<i>Mist Systems</i>
<i>Plain and Roller Contact Bearings</i>	<i>Centrifugal Compressors</i>	<i>Vacuum Pumps</i>
<i>Rotary Screw Compressors</i>	<i>Rotary Vane Compressors</i>	<i>Proofer Ovens</i>
<i>Reciprocating Compressors</i>	<i>Pulp & Paper Machines</i>	<i>Oven Chains</i>

PRODUCT FEATURES:

- 100% Fully Synthetic
- Wide Temperature Ranges
- Excellent Thermal & Oxidative Stability
- Low Pour Points
- High Flash Points
- Premium anti-wear properties provide extended equipment life

PRODUCT PHYSICAL PROPERTIES:

TYPICAL PROPERTIES	TEST METHOD	GEARSYN 150AW	GEARSYN 220AW	GEARSYN 320AW	GEARSYN 460AW	GEARSYN 680AW
ISO Grade	ASTM D2422	150	220	320	460	680
Viscosity @ 40°C,cSt	ASTM D445	156.3	230.4	311.3	486.2	676.7
Viscosity @ 100°C,cSt	ASTM D445	18.29	24.14	29.57	41.37	54.35
Viscosity Index	ASTM D2270	131	131	130	133	140
Flash Point, °C/°F	ASTM D92	260/500	262/504	270/518	270/518	270/518
Pour Point, °C/°F	ASTM D97	-45/-49	-35/-31	-33/-27	-27/-17	-25/-13
Copper Corrosion	ASTM D130	1B	1B	1B	1B	1B
Rust Prevention	ASTM D665	Pass	Pass	Pass	Pass	Pass
Evaporation, %	ASTM D972	<1%	<1%	<1%	<1%	<1%
Specific Gravity	ASTM D1298	0.87	0.87	0.88	0.88	0.88

Petrochem, Inc.

333 North Randall Road St. Charles, IL 60174

Phone (630) 513-6350 **Fax** (630) 513-8324

Web www.petrochem1.com

Email info@petrochem1.com



The information contained herein is believed to be accurate but all suggestions are made without Guarantee because the conditions of actual use are beyond our control. Petrochem, Inc. disclaims all Liability incurred in connection with the use of this data or suggestions.

Member of the American Baking Society